



DATA SHEET (effective 09/22/09)

**AFM-Z (Medium) Continuous Rolls/Sheets**

[Biocide Additive]

**Physical Properties**

Polymer			PVC/NBR (Medium)
Color			Black
Classifications			
ASTM D 1056-68			SCE42/43
ASTM D 1056-07			2C2/2C3
Suffix Requirements			
B2, C1, M			
1. 25% Compression Resistance (psi)	ASTM D 1056	6.0 – 12.0	
2. 50% Compression Set (%)	ASTM D 1056	25 max.	
3. Density (lb/ft <sup>3</sup> )	ASTM D 1056	12.0 to 18.0	
4. Water Absorption (%)	ASTM D 1056	5 max.	
5. Tensile (psi)	ASTM D 412	90 min.	
6. Elongation (%)	ASTM D-412	100 min.	
7. Flammability (1)			
FMVSS302	0 Burn Rate	Pass	
8. Temperature Use °F (2)			
		Cold Crack	-40
		High (3)	200
Standard Roll Widths (in)			38" or 44"
Maximum Gauge (in)			0.625"

(1) Flammability – This item and any corresponding data refer to typical performance in the specific test indicated and should not be construed to imply this material's behavior in other fire conditions.

(2) This recommendation is based on polymer type only. For specific application requirements please contact technical service dept.

(3) This temperature is the maximum allowable for intermittent exposure only. For continuous use temperature please contact technical service department.

PVC = Polyvinyl Chloride

NBR = Acrylonitrile Butadiene Rubber

Minimum gauge for skin two sided products is 3/4"

Other gauges and widths may be available. Please contact Customer Service.

Note: SAEJ 18 is equivalent to ASTM D 1056.

**Seal & Design  
Able Division**

5533 Steeles Avenue West Unit 11  
Toronto, Ontario M9L 1S7  
Ph: (416) 741-0750  
Gasket@AbleSealAndDesign.com

**Seal & Design  
Corporate Headquarters**

4015 Casilio Parkway  
Clarence, NY 14031  
Ph: (716) 759-2222  
Info@SealAndDesign.com  
[www.SealAndDesign.com](http://www.SealAndDesign.com)

**Seal & Design  
Higbee Division**

6741 Thompson Rd N  
Syracuse, NY 13221  
Ph: (315) 432-8021  
Sales@Higbee-Inc.com