



**SUBMITTAL SHEET** (effective 06/08/07)

**CX Continuous Rolls/Sheets**

**Physical Properties**

Polymer			PVC/NBR
Color			Black
Classifications			
ASTM D 1056-68			SBE41
ASTM D 1056-00			2B1
Suffix Requirements			B2, M
1. 25% Compression Resistance (psi)	ASTM D 1056		1.5 to 5
2. 50% Compression Set (%)	ASTM D 1056		25 max.
3. Density (lb/ft <sup>3</sup> )	ASTM D 1056		3 to 6
4. Water Absorption (lb/ft <sup>2</sup> )	ASTM D-1667		0.1 max.
5. Tensile (psi)	ASTM D 412		30 min.
6. Elongation (%)	ASTM D 412		100 min.
7. Flammability (1)			
FMVSS302	0 Burn Rate		Pass
UL 94	V0/5VA @ 1/4"		Pass
ASTM E 84	25/50 up to 1"		Pass
8. Cold Crack @ 28°F (no break)	MIL P 15280J		Pass
9. Temperature Use (2)	ASTM D-1056	Cold Crack High (3)	-40 200
<b>Tubular</b>			
ID (in)			Up to 6"
Maximum Gauge (in)			Up to 1"
Length, feet			6
<b>Sheet</b>			
Standard Roll Widths (in)			48"
Maximum Gauge (in)			Up to 2"

(1) Flammability – This item and any corresponding data refer to typical performance in the specific test indicated and should not be construed to imply this material's behavior in other fire conditions.

(2) This recommendation is based on polymer type only. For specific application requirements please contact technical service

(3) This temperature is the maximum allowable for intermittent exposure only. For continuous use temperature please contact technical service department.

PVC = Polyvinyl Chloride

NBR = Acrylonitrile Butadiene Rubber

Other gauges and widths may be available. Please contact Customer Service.

**Seal & Design  
Able Division**

5533 Steeles Avenue West Unit 11  
Toronto, Ontario M9L 1S7  
Ph: (416) 741-0750  
Gasket@AbleSealAndDesign.com

**Seal & Design  
Corporate Headquarters**

4015 Casilio Parkway  
Clarence, NY 14031  
Ph: (716) 759-2222  
Info@SealAndDesign.com  
www.SealAndDesign.com

**Seal & Design  
Higbee Division**

6741 Thompson Rd N  
Syracuse, NY 13221  
Ph: (315) 432-8021  
Sales@Higbee-Inc.com