

DATA SHEET (effective 08/01/08)

FC0 (Fine Cell) Continuous Rolls/Sheets

Physical Properties

Polymer	PVC/NBR	
Color	Black	
Classifications		
ASTM D 1056-68	ASTM D 1056-68	SBO10
ASTM D 1056-00		1B0
Suffix Requirements		B2, C1, M, P
1. 25% Compression Resistance (psi)	ASTM D 1056	0.4 max.
2. 50% Compression Set (%)	ASTM D 1056	5 max.
3. Density (lb/ft ³)	ASTM D 1056	3.5 – 7.0
4. Tensile (psi)	ASTM D 412	25 min.
5. Elongation (%)	ASTM D 412	125 min.
6. Flammability (1)		
FMVSS302	0 Burn Rate	Pass
UL 50		Pass
UL 94	HF-1 @ 3.9 mm	Pass
	V0 @ 2.8 mm	Pass
	5VA @ 3.8 mm	Pass
	5VB @ 2.8 mm	Pass
7. Temperature Use: (2)	ASTM D 1056	Cold Crack High (3)
		-40°F 200
8. Thermal Conductivity	ASTM C 518	
BTU-in/hr • sq.ft. • °F (W/mK)		0.279 (0.040)
75°F mean temp (24°C)		
Standard Roll Widths (in)		54"
Maximum Gauge (in)		1.57" (40 mm)

(1) Flammability – This item and any corresponding data refer to typical performance in the specific test indicated and should not be construed to imply this material's behavior in other fire conditions.

(2) This recommendation is based on polymer type only. For specific application requirements please contact technical service

(3) This temperature is the maximum allowable for intermittent exposure only. For continuous use temperature please contact technical service department.

NBR – Acrylonitrile Butadiene Rubber

PVC – Polyvinyl Chloride

Minimum gauge for skin two sided products is 1/4"

Other gauges and widths may be available. Please contact Customer Service.

Note: FC0 meets: GMN11106 Type IAA

GMN11101

**Seal & Design
Able Division**

5533 Steeles Avenue West Unit 11
Toronto, Ontario M9L 1S7
Ph: (416) 741-0750
Gasket@AbleSealAndDesign.com

**Seal & Design
Corporate Headquarters**

4015 Casilio Parkway
Clarence, NY 14031
Ph: (716) 759-2222
Info@SealAndDesign.com
www.SealAndDesign.com

**Seal & Design
Higbee Division**

6741 Thompson Rd N
Syracuse, NY 13221
Ph: (315) 432-8021
Sales@Higbee-Inc.com