



**DATA SHEET** (effective 02/12/09)

**IG1** Continuous Rolls/Sheets

**Physical Properties**

Polymer	PVC/NBR/CR	
Color	Black	
Classifications		
ASTM D 1056-68		SBE41
ASTM D 1056-07		2B1
Suffix Requirements		B2, C1, M
1. 25% Compression Resistance (psi)	ASTM D 1056	2 to 5
2. 50% Compression Set (%)	ASTM D 1056	25 max.
3. Density (lb/ft <sup>3</sup> )	ASTM D 1056	4 to 6
4. Water Absorption (%)	ASTM D 1056	10 max.
5. Tensile (psi)	ASTM D 412	50 min.
6. Elongation (%)	ASTM D-412	75 min.
7. Flammability (1)		
FMVSS302	0 Burn Rate	Pass
UL 94	V/0/5VA@ 6.2 mm	Pass
UL 94	HF-1 @ 1.5 mm	Pass
8. C-Tear Strength (lbs/in.)	ASTM D-624 Die C	10 min.
9. Temperature Use °F (2)	ASTM D-1056	Cold Crack High (3)
		-40 200
Standard Roll Widths (in)		54"
Maximum Gauge (in)		1-1/4"

(1) Flammability – This item and any corresponding data refer to typical performance in the specific test indicated and should not be construed to imply this material's behavior in other fire conditions.

(2) This recommendation is based on polymer type only. For specific application requirements please contact technical service

(3) This temperature is the maximum allowable for intermittent exposure only. For continuous use temperature please contact technical service department.

PVC = Polyvinyl Chloride

NBR = Acrylonitrile Butadiene Rubber

CR = Chloroprene (Neoprene®)

Minimum gauge for skin two sided products is 3/4"

Other gauges and widths may be available. Please contact Customer Service.

Note: SAEJ 18 is equivalent to ASTM D-1056.

**Seal & Design  
Able Division**

5533 Steeles Avenue West Unit 11  
Toronto, Ontario M9L 1S7  
Ph: (416) 741-0750  
Gasket@AbleSealAndDesign.com

**Seal & Design  
Corporate Headquarters**

4015 Casilio Parkway  
Clarence, NY 14031  
Ph: (716) 759-2222  
Info@SealAndDesign.com  
www.SealAndDesign.com

**Seal & Design  
Higbee Division**

6741 Thompson Rd N  
Syracuse, NY 13221  
Ph: (315) 432-8021  
Sales@Higbee-Inc.com