



**DATA SHEET** (effective 05/28/08)

**IV3 Continuous Rolls/Sheets**

**Physical Properties**

Polymer			PVC/NBR/CR
Color			Black
Classifications			
ASTM D 1056-68			SBE43
ASTM D 1056-07			2B3
Suffix Requirements			B3, C1, F1, M
1. 25% Compression Resistance (psi)	ASTM D 1056		9.0 – 13.0
2. 50% Compression Set (%)	ASTM D 1056		35 max.
3. Density (lb/ft <sup>3</sup> )	ASTM D 1056		7.0 – 9.5
4. Water Absorption (lb/ft <sup>2</sup> )	ASTM D 1667		0.1 max.
5. Tensile (psi)	ASTM D 412		100 min.
6. Elongation (%)	ASTM D 412		100 min.
7. Flammability (1)			
FMVSS302	0 Burn Rate		Pass
UL 94	HF-1 @ 1/16"		Pass
UL 94	V-0/5VA @ 1/4"		Pass
FAR 25.853 a(2003)	@ 1/4"		Pass
8. Temperature Use: (2)	ASTM D 1056	Cold Crack High (3)	-40°F 200
Standard Roll Widths (in)			54"
Maximum Gauge (in)			1.5"

(1) Flammability – This item and any corresponding data refer to typical performance in the specific test indicated and should not be construed to imply this material's behavior in other fire conditions.

(2) This recommendation is based on polymer type only. For specific application requirements please contact technical service

(3) This temperature is the maximum allowable for intermittent exposure only. For continuous use temperature please contact technical service department.

NBR – Acrylonitrile Butadiene Rubber

PVC – Polyvinyl Chloride

CR – Chloroprene (Neoprene®)

Minimum gauge for skin two sided products is 3/4"

Other gauges and widths may be available. Please contact Customer Service.

Note: SAEJ 18 is equivalent to ASTM D-1056

**Seal & Design  
Able Division**

5533 Steeles Avenue West Unit 11  
Toronto, Ontario M9L 1S7  
Ph: (416) 741-0750  
Gasket@AbleSealAndDesign.com

**Seal & Design  
Corporate Headquarters**

4015 Casilio Parkway  
Clarence, NY 14031  
Ph: (716) 759-2222  
Info@SealAndDesign.com  
[www.SealAndDesign.com](http://www.SealAndDesign.com)

**Seal & Design  
Higbee Division**

6741 Thompson Rd N  
Syracuse, NY 13221  
Ph: (315) 432-8021  
Sales@Higbee-Inc.com