







SUBMITTAL SHEET (effective 06/08/07)



·			
Physical Properties			
Polymer			CR
Color			Black
Classifications			
ASTM D 1056-68			SCE42/43
ASTM D 1056-00			2C2/2C3
Suffix Requirements			B2, M
1. 25% Compression Resistance (psi)	ASTM D 1056		6.0 - 13.0
2. 50% Compression Set (%)	ASTM D 1056		25 max.
3. Density (lb/ft ³)	ASTM D 1056		15 – 25
4. Water Absorption (lb/ft2)	ASTM D 1667		0.1 max.
5. Tensile (psi)	ASTM D 412		100 min.
6. Elongation (%)	ASTM D 412		200 min.
7. Flammability (1)			
FMVSS302	0 Burn Rate		Pass
8. Temperature Use: (2)	ASTM D 1056	Cold Crack	-20°F
		High (3)	200
Standard Roll Widths (in)			36"
Maximum Gauge (in)			3/8"

imply this material's behavior in other fire conditions.

CR - Chloroprene (Neoprene®)

Other gauges and widths may be available. Please contact Customer Service.

Note: SAEJ 18 is equivalent to ASTM D-1056

⁽²⁾ This recommendation in based on polymer type only. For specific application requirements please contact technical service
(3) This temperature is the maximum allowable for intermittent exposure only. For continuous use temperature please contact technical service department.