



# DuPont™ Kalrez® Spectrum™ 0040

For Low-Temperature Applications

Technical Information — Rev. 2, June 2011

## Product Description

Kalrez® Spectrum™ 0040 perfluoroelastomer parts are specifically designed for low-temperature environments where significant chemical resistance is required. Proprietary polymer and cure technology promotes low-temperature sealing performance (-42°C) of Kalrez® Spectrum™ 0040 parts to temperatures typically unattainable for perfluoroelastomers parts. Kalrez® Spectrum™ 0040 is an excellent choice in applications such as couplings for the chemical transportation industry, or for other applications where chemical resistance and elasticity are required in some of the coldest environments. The volume swell for Kalrez® Spectrum™ 0040 is approximately 10% when exposed to nitric acid at 110°C for 168 hours. Compression set resistance is similar to that of our broad chemically-resistant product, Kalrez® Spectrum™ 6375.

### Typical Physical Properties <sup>1</sup>

Color	Black
Hardness, Durometer Shore A <sup>2</sup>	70
100% Modulus <sup>3</sup> , MPa (psi)	5.17 (750)
Tensile Strength at Break <sup>3</sup> , MPa (psi)	8.96 (1300)
Elongation at Break <sup>3</sup> , %	170
Compression Set <sup>4</sup> , %	
70 hrs. at 200°C (392°F)	41
336 hrs. at 200°C (392°F)	57
672 hrs. at 200°C (392°F)	62
Upper Service Temperature, °C (°F) <sup>5</sup>	220 (428)
Lower Service Temperature, °C (°F) <sup>5</sup>	-42 (-43.6)
Tg °C (°F) <sup>5</sup>	-27 (-16.6)
Tr10 °C (°F) <sup>6</sup>	-17(1.4)
<u>Volume Swell (% Change)<sup>7</sup>, 168 hours</u>	
Nitric Acid, 110°C (230°F)	10
Ethylenediamine, 194°F (90°C)	19

<sup>1</sup>Not to be used for specification purposes

<sup>2</sup>ASTM D2240 (pellet test specimens)

<sup>3</sup>ASTM D412 500mm/min (dumbbell test specimens)

<sup>4</sup>ASTM D395B (AS568 K214 O-ring test specimens)

<sup>5</sup>DuPont proprietary test method

<sup>6</sup>ASTM D1329 (slab test specimens)

<sup>7</sup>ASTM D471 (AS568 K214 O-ring test specimens)



#### Seal & Design Able Division

5533 Steeles Avenue West Unit 11  
Toronto, Ontario M9L 1S7  
Ph: (416) 741-0750  
Gasket@AbleSealAndDesign.com

#### Seal & Design Corporate Headquarters

4015 Casilio Parkway  
Clarence, NY 14031  
Ph: (716) 759-2222  
Info@SealAndDesign.com  
www.SealAndDesign.com

#### Seal & Design Higbee Division

6741 Thompson Rd N  
Syracuse, NY 13221  
Ph: (315) 432-8021  
Sales@Higbee-Inc.com