



DuPont™ Kalrez® 3065

Technical Information — Rev. 3, July 2010

Product Description

DuPont™ Kalrez® 3065 is a highly-filled product containing carbon black and fiber reinforcement, designed to function without extrusion under extreme pressure. It has good all round chemical resistance and excellent resistance to sour oil and amines. Kalrez® 3065 has an upper service temperature of 288 °C (550 °F).

The mechanical properties and chemical resistance of Kalrez® 3065 make it the best choice for many oil and gas well applications. In these applications it is normally used in the form of V-rings and other custom parts rather than O-rings.

The physical properties of Kalrez® 3065 are as follows:

Typical Physical Properties¹

Hardness ² , Shore A (pellets) ± 5	90
100% Modulus ³ , MPa (psi)	N/A ⁷
Tensile Strength at Break ³ , MPa (psi)	24.10 (3495)
Elongation at Break ³ , %	30
Compression Set ⁴ , 70 hr at 204 °C (400 °F), %	N/A
Brittle Point ⁵ , °C	-23
Maximum continuous service temperature ⁶ , °C (°F)	288 (550)

¹ Not to be used for specifications

² ASTM D2240

³ ASTM D412, 500 mm/min (20/μm)

⁴ ASTM D395 B, pellets

⁵ ASTM D746

⁶ DuPont Performance Polymers proprietary test method

⁷ N/A = Not applicable



The miracles of science™

Chemical Resistance	DuPont™ Kalrez® 3065
Aromatic/Aliphatic oils	+++
Acids	++
Alkalis	++
Alcohols	+++
Aldehydes	+++
Amines	+++
Ethers	+++
Esters	+++
Ketones	+++
Steam/Hot Water	++
Strong Oxidizers	0
Ethylene/Propylene Oxide	--

+++ = Excellent ++ = Very Good + = Good 0 = Marginal -- = Poor --- = Not Recommended



**Seal & Design
Able Division**
5533 Steeles Avenue West Unit 11
Toronto, Ontario M9L 1S7
Ph: (416) 741-0750
Gasket@AbleSealAndDesign.com



**Seal & Design
Corporate Headquarters**
4015 Casilio Parkway
Clarence, NY 14031
Ph: (716) 759-2222
Info@SealAndDesign.com
www.SealAndDesign.com



**Seal & Design
Higbee Division**
6741 Thompson Rd N
Syracuse, NY 13221
Ph: (315) 432-8021
Sales@Higbee-Inc.com