



Technical Information — Rev. 3, July 2010

Product Description

DuPont™ Kalrez® Spectrum™ 6380 perfluoroelastomers parts are a non-black product specifically developed for chemical processes involving hot, aggressive amines. In addition, it has excellent overall chemical resistance (see chart below). This cream colored product is easily identifiable when selecting an O-ring material for harsh chemical plant services. This material has excellent mechanical properties and is a top choice for both static and dynamic sealing applications. A maximum continuous service temperature of 225 °C is suggested while short-term excursions to higher temperatures are permissible.

For more information on Kalrez® Spectrum™ 6380, or to see if it might be right for your difficult sealing applications in amines and other aggressive chemical streams, please contact DuPont.

Typical Physical Properties¹

Hardness, Shore A ² ±5	80
100% Modulus ³ , MPa (psi)	6.89 (1000)
Tensile Strength at Break ³ , MPa (psi)	15.86 (2300)
Elongation at Break ³ , %	160
Compression Set ⁴ , 70 hr at 204 °C, %	40

¹ Not to be used for specification purposes

² ASTM D2240

³ ASTM D412, 500 mm/min (20 in/min)

⁴ ASTM D395B, size 214 O-ring

Chemical Resistance (672 hour exposure)

Material Compound	DuPont™ Kalrez® Spectrum™ 6380	
<i>Chemical Resistance to:</i>	<i>Temperature, °C</i>	<i>Rating</i>
Acetic Acid	100	A
Nitric Acid (fuming)	60	A
Diethyl Amine	50	A
Monoethanolamine	150	B
Ethylene Diamine	90	A
Butyraldehyde	70	A
Methanol	100	A
Toluene	100	A
Water	225	A

Rating: A: < 10% volume change and minimal effect on elastomer properties
 B: 10–20% volume increase and slight effect on elastomer properties
 C: > 20% volume increase and significant effect on elastomer properties
 X: Elastomer not recommended for this service



Seal & Design
Corporate Headquarters
 Ph: (716)-759-3344
 Info@SealAndDesign.com
www.SealAndDesign.com