



DuPont™ Kalrez® 8575

For Semiconductor Processes

Technical Information—Rev. 8, June 2011

Product Description

DuPont™ Kalrez® 8575 perfluoroelastomer parts are a white product for “select” etch, ash/strip and deposition process applications. It offers very low weight loss in oxygen and fluorine-based plasmas, low outgassing, and excellent elastic recovery properties. Kalrez® 8575 has excellent vacuum and long-term sealing performance, good mechanical properties and is well-suited for both static and dynamic sealing applications (e.g., gas inlets, chamber lid seals, slit valve doors). A maximum continuous service temperature of 300 °C is suggested. Ultrapure post-cleaning and packaging is standard for all parts made of Kalrez® 8575.

Key Performance Features Contribute to Extended Seal Life

- Excellent resistance to oxygen and fluorine-based plasmas, as well as chlorinated cleaning gasses (e.g., ClF_3)
- Very low weight loss in reactive plasmas
- Very low outgassing properties
- Excellent (low) compression set properties
- Excellent elastic recovery properties

Suggested Applications

- Chamber lids
- Gas inlets
- Quartz windows
- Throttle valves
- Other plasma applications

Typical Physical Properties¹

Color	White
Hardness, Shore A (pellet) ²	62
Hardness, Shore M (O-ring) ³	72
100% Modulus ⁴ , MPa	2.47
Tensile Strength at Break ⁴ , MPa	12.04
Elongation at Break ⁴ , %	230
Compression Set ⁵ , %, 70 hr at 204 °C	29
Max. Continuous Service Temperature ⁶ , °C	300

¹ Not to be used for specification purposes

² ASTM D2240 (pellet test specimens)

³ ASTM D2240 and ASTM D1414 (AS568 K214 O-ring test specimens)

⁴ ASTM D412 test method (dumbbell test specimens)

⁵ ASTM D395B (pellet test specimens)

⁶ DuPont proprietary test method

Fabs Choose Kalrez® 8575 for Improved Performance

Kalrez® 8575 has been reported to significantly improve wafer production in semiconductor etching and ashing applications. In evaluations by a fabline customer, Kalrez® 8575 exhibited longer seal life compared to a competitive perfluoroelastomer in both dynamic and static sealing applications.



The miracles of science™

Case Report #1

Customer	U.S. East Coast Fabline
Equipment	TEL Unity
Process Type	Deep Trench Etch
Components	End Point Window Seal (229 O-ring) (most difficult location for seal performance)
Process Gasses	HBr, O ₂ , SF ₆ , NF ₃
Rf Power	1500 Watts
Process Temperature	~70 °C
Incumbent Material	Competitive FFKM A2
Incumbent Performance	After 6 months, fluoroelastomer was half eroded, competitive FFKM became brittle, developed cracks and leaked
DuPont™ Kalrez® 8575 Performance:	Evaluated in application for over 10 months without failure Based upon this success, customer evaluated complete seal set (15 sizes) and has changed all competitive FFKM to DuPont™ Kalrez® 8575



**Seal & Design
Able Division**
5533 Steeles Avenue West Unit 11
Toronto, Ontario M9L 1S7
Ph: (416) 741-0750
Gasket@AbleSealAndDesign.com



**Seal & Design
Corporate Headquarters**
4015 Casilio Parkway
Clarence, NY 14031
Ph: (716) 759-2222
Info@SealAndDesign.com
www.SealAndDesign.com



**Seal & Design
Higbee Division**
6741 Thompson Rd N
Syracuse, NY 13221
Ph: (315) 432-8021
Sales@Higbee-Inc.com