



## Leader Style 978

### Rubberbonded Fiber Jointing Sheets

#### DESCRIPTION

Black in color  
manufactured using NBR and  
aramid/inorganic fiber.

#### APPLICATION

General purpose material  
suitable for use in a wide  
range of applications, including  
hot and cold water, steam, oils,  
fuels, gases and a wide range  
of general chemicals.

#### TEMPERATURE

Max. Intermittent  
Temperature Rating: 700 F  
Max. Continuous Temperature  
Rating: 400 F

#### TECHNICAL DATA

density [g/cm <sup>3</sup> ]	2
M-Value	3.5
Y- Value [psi]	2000
ASTM F36 Recovery [% min]	50
Max Pressure Rating [psi]	1000
Max P x T	350.000
compressability, [ASTM F36], [%]	7-17
ASTM F37 Sealability [ml/min] Sg=1000 psi=30	0,04
BS 7531 Gas Leakage [ml/min]	<1.0
ASTM F38 Creep Relaxation [%]	27
BS 7531 Residual Stress [mpa]	23
ASTM F152 Average Tensile [psi]	2100
IRM 903 @ 300 oF Thickness Increase [%]	0 - 10
ASTM Fuel B @ 70-85 oF Weight Increase [%]	20 max.
Rubber Binder	NBR



**Seal & Design**  
Able Division  
5533 Steeles Avenue West Unit 11  
Toronto, Ontario M9L 1S7  
Ph: (416) 741-0750  
Gasket@AbleSealAndDesign.com



**Seal & Design**  
Corporate Headquarters  
4015 Casilio Parkway  
Clarence, NY 14031  
Ph: (716) 759-2222  
Info@SealAndDesign.com  
[www.SealAndDesign.com](http://www.SealAndDesign.com)



**Seal & Design**  
Higbee Division  
6741 Thompson Rd N  
Syracuse, NY 13221  
Ph: (315) 432-8021  
Sales@Higbee-Inc.com