



# Leader NA-59

## Rubberbonded Fiber Jointing Sheets

### DESCRIPTION

NA-59 is a compressed NBR/Aramid Fiber Sheet

### APPLICATION

Recommended for general service gaskets on all machinery and process piping and equipment.

### TEMPERATURE

Max. Intermittent Temperature Rating: 350 F  
Max. Continuous Temperature Rating: 400 F

### TECHNICAL DATA

Standard Temperature Rating [°F]	350
density [g/cm <sup>3</sup> ]	1.75
ASTM F36 Recovery [% min]	50
Standard Pressure Rating [psi]	1000
compressability, [ASTM F36], [%]	7 - 17
ASTM F37 Sealability [ml/min] Sg=1000 psi=30	<1.0
BS 7531 Gas Leakage [ml/min]	<1.0
ASTM F38 Creep Relaxation [%]	40
BS 7531 Residual Stress [mpa]	17
ASTM F152 Average Tensile [psi]	1800
Rubber Binder	NBR



**Seal & Design**  
Able Division  
5533 Steeles Avenue West Unit 11  
Toronto, Ontario M9L 1S7  
Ph: (416) 741-0750  
Gasket@AbleSealAndDesign.com



**Seal & Design**  
Corporate Headquarters  
4015 Casilio Parkway  
Clarence, NY 14031  
Ph: (716) 759-2222  
Info@SealAndDesign.com  
[www.SealAndDesign.com](http://www.SealAndDesign.com)



**Seal & Design**  
Higbee Division  
6741 Thompson Rd N  
Syracuse, NY 13221  
Ph: (315) 432-8021  
Sales@Higbee-Inc.com