



Leader NA-60

Rubberbonded Fiber Jointing Sheets

DESCRIPTION

NA-60 is a low cost, NBR/Aramid fiber, compressed gasket sheet made with all the great features of premium gasket materials without the cost. Nothing is left out, only the best raw materials are used, without compromise. NA-60 is recommended for general service gaskets on all machinery and process piping and equipment.

APPLICATION

Can be used for general service gaskets on all machinery, process piping and equipment.

TEMPERATURE

Max. Intermittent Temperature Rating: 700 F
Max. Continuous Temperature Rating: 400 F

TECHNICAL DATA

density [g/cm ³]	1.87
M-Value	3.5
Y- Value [psi]	2000
ASTM F36 Recovery [% min]	40
ROTT [Gb]	1496
Max Pressure Rating [psi]	1000
Max P x T	350.000
compressability, [ASTM F36], [%]	7 - 17
ASTM F37 Sealability [ml/min] Sg=1000 psi=30	0,04
BS 7531 Gas Leakage [ml/min]	<1.0
ASTM F38 Creep Relaxation [%]	27
BS 7531 Residual Stress [mpa]	17
ASTM F152 Average Tensile [psi]	2100
IRM 903 @ 300 oF Thickness Increase [%]	0 - 10
ASTM Fuel B @ 70-85 oF Weight Increase [%]	20 max.
Rubber Binder	NBR



Seal & Design
Able Division
5533 Steeles Avenue West Unit 11
Toronto, Ontario M9L 1S7
Ph: (416) 741-0750
Gasket@AbleSealAndDesign.com



Seal & Design
Corporate Headquarters
4015 Casilio Parkway
Clarence, NY 14031
Ph: (716) 759-2222
Info@SealAndDesign.com
www.SealAndDesign.com



Seal & Design
Higbee Division
6741 Thompson Rd N
Syracuse, NY 13221
Ph: (315) 432-8021
Sales@Higbee-Inc.com