

## SSP-1529

# Semi-Conductive Silicone Compound

### PRODUCT DESCRIPTION

SSP-1529 is a 65 durometer semi-conductive silicone compound. This product is supplied as fully cured, conductive sheet stock or ready-to-mold compound. The data below was generated using ASTM test method and procedures.

DATA	Typical Values
Shore A (60-70 range)	65
Tensile psi (500 minimum)	1000 psi
Elongation % (150 minimum)	200%
Compression Set %	7.5%
Specific Gravity	1.17
Volume Resistivity ohm / cm (10 max)	7 ohm /cm
Color	Black
Thermal Stability Range	-60°C - 220°C

### STORAGE

Store in a cool, dry environment.

### SHELF LIFE

The shelf life of SSP1529 is 2 months. Cold storage may extend shelf life.

### HANDLING & SAFETY

MSDS information is available on request.



**Seal & Design  
Able Division**  
5533 Steeles Avenue West Unit 11  
Toronto, Ontario M9L 1S7  
Ph: (416) 741-0750  
Gasket@AbleSealAndDesign.com



**Seal & Design  
Corporate Headquarters**  
4015 Casilio Parkway  
Clarence, NY 14031  
Ph: (716) 759-2222  
Info@SealAndDesign.com  
www.SealAndDesign.com



**Seal & Design  
Higbee Division**  
6741 Thompson Rd N  
Syracuse, NY 13221  
Ph: (315) 432-8021  
Sales@Higbee-Inc.com

Because we cannot foresee or control varied conditions, under which this information and our materials may be used, we do no guarantee the applicability or accuracy of this information or the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose or nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents.