

PRODUCT DESCRIPTION

The SSP502- Series is a nickel coated graphite filled silicone elastomer. This series includes Shore A values which range from 30 to 70. These products are supplied as ready-to-mold compound; fully cured, conductive sheet stock; or, for some formulations, continuous rolls. The data below was generated using ASTM test methods and procedures.

<u>Product</u>	Shore A	Tensile (psi)	Elongation (%)	Tear B (ppi)	Max V.R. (ohm/cm)	Specific Gravity	Availability
SSP502-30	33	100	400	N/A	1.5	1.65 - 1.85	MC, SS
SSP502-40	45	150	200	25	0.030	1.80 - 2.20	MC, SS, CR
SSP502-55	55	150	200	25	0.040	1.90 - 2.05	MC, SS, CR
SSP502-65	65	200	200	35	0.040	1.90 - 2.05	MC, SS, CR
SSP502-75	75	270	250	35	0.040	1.95 - 2.05	MC, SS

CATALYZING

Raw material available catalyzed and ready for press cure molding. Data above was generated with Varox catalyst system.

SHELF LIFE

Uncatalyzed – indefinite, may need freshening after 1-2 years. Catalyzed – 6 months. Cold storage will extend shelf life.

HANDLING & SAFETY

MSDS information is available on request.



**Seal & Design
Able Division**
5533 Steeles Avenue West Unit 11
Toronto, Ontario M9L 1S7
Ph: (416) 741-0750
Gasket@AbleSealAndDesign.com



**Seal & Design
Corporate Headquarters**
4015 Casilio Parkway
Clarence, NY 14031
Ph: (716) 759-2222
Info@SealAndDesign.com
www.SealAndDesign.com



**Seal & Design
Higbee Division**
6741 Thompson Rd N
Syracuse, NY 13221
Ph: (315) 432-8021
Sales@Higbee-Inc.com

Because we cannot foresee or control varied conditions, under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose or nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents.