



Sealing for a safer and greener tomorrow

NA1082SAN



www.SealAndDesign.com

Compressed Sheet Sanitary Service Gasket Material

Application:

Drinking Water Service:

Teadit style NA1082SAN is developed to allow compliance for drinking water system components with NSF-61, from source to tap. Certification to NSF-61 provides assurance to a highest level that NA1082SAN is safe for use in drinking water service. The gasket material was also tested and found to be in conformance per US FDA 21 CFR 177.2600.

Isolation:

An added benefit is that Teadit style 1082SAN has a strong dielectric rating, making it ideal for isolation kit applications where compressed fiber sheet gaskets can be utilized.

Construction:

Teadit style NA1082SAN is specifically formulated to pass criteria established in NSF-61 for sealing materials, as well as providing excellent resistance to conductivity. Compressed Fiber Sheet technology provides mechanical and service characteristics unmatched by standard elastomeric grades.

Availability	Size: 59 x 63 in 59 x 126 in*
	Thickness: 1/64", 1/32", 1/16", 1/8"
Temperature	Continuous Service: 500°F (260°C)
	Maximum Service: 752°F (400°C)
Pressure	Continuous Service: 1160 psi (80 bar)
	Maximum Service: 1595 psi (110 bar)
Color	Blue
ASTM F104	F712120E12M5

*available on special request



Typical Physical Properties:

Dielectric Strength - ASTM D149	18.5 kv/mm (1/16" thk)
Density	121 lb/ft ³ (1.95 g/cm ³)
After 1 hour at 210°F (100°C)	
Compressibility - ASTM F36 J	5-15%
Recovery - ASTM F36 J	50%
Tensile Strength Across Grain - ASTM F152	1885 psi (13N/mm ²)
Thickness Increase - ASTM F146	
ASTM Oil IRM903 Nr. 3 5h / 300 °F (150°C)	15%
Fuel B, 5h / 77 °F (25°C)	10%
Weight Increase - ASTM F146	
ASTM Oil IRM903 Nr. 3 5h / 300 °F (150°C)	15%
Fuel B, 5h / 77 °F (25°C)	10%



Certified to
NSF/ANSI 61



Seal & Design
Corporate Headquarters
Ph: (716)-759-3344
Info@SealAndDesign.com
www.SealAndDesign.com