

AB-366



18-03

FEATURES

- FDA Grade and Dairy 3A Specs
- Excellent resistance to petroleum-based hydraulic fluids
- Wide range of service temperatures
- Very good resistance to alkalis and acids
- ASTM Grade

GRADE	Industrial
FINISH	Smooth
POWDER	No
TRIMMED	Yes
COLOR	White

	GAUGE IN (MM)	WIDTH IN (MM)	SURFACE/ROLL SFT (M ²)	LENGTH/ROLL LFT (M)	WEIGHT/ROLL LBS (KG)
307-04-362	1/16 (1.59)	36 (914.4)	300 (27.87)	100 (30.48)	129 (58.5)
307-04-482	1/16 (1.59)	48 (1219.2)	400 (37.16)	100 (30.48)	171 (77.6)
307-06-362 ¹	3/32 (2.38)	36 (914.4)	225 (20.9)	75 (22.85)	147 (66.7)
307-08-362	1/8 (3.7)	36 (914.4)	150 (13.93)	50 (15.24)	129 (58.5)
307-08-482	1/8 (3.7)	48 (1219.2)	200 (18.58)	50 (15.24)	171 (77.6)
307-12-362	3/16 (4.76)	36 (914.4)	120 (11.15)	40 (12.19)	152 (68.9)
307-12-482	3/16 (4.76)	48 (1219.2)	160 (14.86)	40 (12.19)	202 (91.6)
307-16-362	1/4 (6.35)	36 (914.4)	120 (11.15)	40 (12.19)	206 (93.4)
307-16-482	1/4 (6.35)	48 (1219.2)	160 (14.86)	40 (12.19)	274 (124.3)
307-24-482	3/8 (9.52)	48 (1219.2)	120 (11.15)	30 (9.14)	309 (140.2)
307-32-482	1/2 (12.70)	48 (1219.2)	120 (11.15)	30 (9.14)	417 (189.2)

¹ Made to order



TECHNICAL SPECIFICATIONS AB-366



18-03

SPECIFICATION ASTM D2000 : 1BF610 meets FDA requirements
POLYMER : NBR/SBR (White)

ASTM	DESCRIPTION	VALUE
	SPECIFIC GRAVITY (gr/cc)	1.4
D2240	HARDNESS (Shore A)	60
D412	TENSILE (psi)	1000 min.
	ULTIMATE ELONGATION (%)	300 min.
D395B	COMPRESSION SET	22 hrs @ 100°C 50% max.
D573	HEAT AGING	70 hrs @ 100°C Changed Hardness: +/- 15 points max. Tensile: +/- 30% max. Elongation: -50% max.
D471	OIL AGING (#3)	70 hrs @ 100°C Changed Volume: 60% max.
TEMPERATURE RANGE (general guideline)		-40° to 200° F -40° to 93°C

Maximum pieces per roll : 2

Minimum piece length : 10'

Width tolerance: -0 / + 1"

Length tolerance: +/- 10%

Material is within RMA commercial gauge tolerances.

Please ensure the product meets your application specification prior to order placement.
Specifications are subject to change without notice. The website version prevails.



Seal & Design
Corporate Headquarters
Ph: (716)-759-3344
Info@SealAndDesign.com
www.SealAndDesign.com