

8500 Aramid-Inorganic/NBR Rubber Binder

COMPRESSED SHEET GASKET MATERIAL § ASTM F104: F712120-A9B3E12K5L151M6



application:

Our workhorse material, DURLON® 8500 is excellent in steam, natural gas, soybean processing and with new generation refrigerants. A high quality general service gasket material for use in a wide range of services in pulp and paper, food, beverage, pharmaceutical, chemical, refinery, gas pipeline and general industry. DURLON® 8500 exhibits good compressibility and recovery, excellent sealability, flexibility and cutting characteristics.

composition:

DURLON® 8500 contains high-strength aramid and inorganic fibers bonded with high-grade Nitrile (NBR) rubber.

fire testing:

DURLON® 8500 has successfully passed a modified version of the API 607 fire test. The duration of the direct flame portion of the test is 30 minutes and the flange temperature must reach 1200°F in the first 15 minutes. The internal pressure is held at a constant 30 psig. After the flame is shut off, the fixture is immediately water quenched with an overhead water blast. Leakage must not exceed 100 ml/min after a 6 minute cool down to successfully pass the test. Subsequent leakage testing is also performed.

anti-stick properties:

Much effort has gone into improving the anti-stick release agents of all compressed DURLON® products. All DURLON® compressed gasket materials have passed the MIL-G-24696B Navy Adhesion Test (366°F/48 hrs).

typical properties:

| | |
|---|--|
| Color: | Green, branded |
| Fiber: | Aramid/Inorganic |
| Binder: | Nitrile (NBR) |
| Fluid Services: | Saturated Steam, Oils, Fuels, Dilute Acids & Alkalis, Solvents, Refrigerants |
| Density: | 1.7 g/cm ³ (106 lbs./ft ³) |
| Tensile Strength, ASTM F152: | 2,000 psi (13.8 MPa) |
| Compressibility, ASTM F36: | 8 to 16% |
| Recovery ASTM F36: | 50% |
| Temperature Range: | -100 to 700°F (-73 to 371°C) |
| Continuous, max: | 548°F (287°C) |
| Pressure, max (ambient temperature): | 1500 psig (103 bar) |
| Fluid Resistance - ASTM F146 IRM 903 oil, 5 h/300°F (149°C) Thickness Increase: | 0 to 15% |
| Weight Increase: | 15% |
| ASTM Fuel B 5 h/70°F (21°C) Thickness Increase: | 0 to 10% |
| Weight Increase: | 10% |
| Sealability ASTM F37 (Fuel A): | 0.01 mL/hr |
| ASTM F37 (Nitrogen): | 0.4 mL/hr |
| Volume Resistivity, ASTM D257: | 4.2 x 10 ¹³ ohm-cm |
| Dielectric Breakdown, ASTM D149: | 11.7 kV/mm (297 V/mil) |
| ASTM F2378 Gas Permeability: | 0.03 cc/min |
| Creep Relaxation ASTM F38: | 20% |
| Flexibility, ASTM F147: | 10x |
| ASTM F104 Line Call-Out: | F712120-A9B3E12K5L151M6 |

Note: ASTM properties based on 1/16" sheet thickness except ASTM F38, which is based on 1/32" sheet thickness. This is a general guide only and should not be the sole means of accepting or rejecting this material. The data listed here falls within the normal range of product properties but should not be used to establish specification limits nor used alone as the basis of design.

m&y and proposed astm gasket constants:

| THICKNESS | 1/16" | 1/8" |
|---|-------------|-------------|
| M | 2.7 | 4.2 |
| Y psi (MPa) | 2359 (16.3) | 2931 (20.2) |
| Gasket Constants | | |
| Gb psi (MPa) | 650 (4.5) | 400 (2.8) |
| a | 0.330 | 0.350 |
| Gs psi (MPa) | 200 (1.4) | 20 (0.1) |
| *Gasket Constants based on proposed ASTM Draft 10.1 | | |

available sheet sizes:

| Nominal Thickness | Sheet Sizes | | Order Code | Sheets Per Roll | Approx. Weight/Sheet lbs (kg) |
|-------------------|-------------|-------------|--------------|-----------------|-------------------------------|
| | inches | mm | | | |
| 1/64" 0.5mm | 60 x 63 | 1524 x 1600 | DG05-060-063 | 20 | 3 (1.4) |
| | 60 x 126 | 1524 x 3200 | DG05-060-126 | 10 | 7 (3.2) |
| 1/32" 0.8mm | 60 x 63 | 1524 x 1600 | DG08-060-063 | 20 | 7 (3.2) |
| | 60 x 126 | 1524 x 3200 | DG08-060-126 | 10 | 14 (6.4) |
| 1.0mm | 60 x 63 | 1524 x 1600 | DG10-060-063 | 20 | 9 (4.1) |
| | 60 x 126 | 1524 x 3200 | DG10-060-126 | 10 | 19 (8.6) |
| | 120 x 126 | 3048 x 3200 | DG10-120-126 | 5 | 37 (16.8) |
| 1/16" 1.5mm | 60 x 63 | 1524 x 1600 | DG15-060-063 | 10 | 14 (6.4) |
| | 60 x 126 | 1524 x 3200 | DG15-060-126 | 5 | 28 (12.7) |
| | 120 x 126 | 3048 x 3200 | DG15-120-126 | 2 | 55 (25.0) |
| 2.0mm | 60 x 63 | 1524 x 1600 | DG20-060-063 | 10 | 18 (8.2) |
| | 60 x 126 | 1524 x 3200 | DG20-060-126 | 5 | 38 (17.2) |
| | 120 x 126 | 3048 x 3200 | DG20-120-126 | 2 | 74 (33.6) |
| 3/32" 2.5mm | 60 x 63 | 1524 x 1600 | DG25-060-063 | 8 | 22 (10.0) |
| | 60 x 126 | 1524 x 3200 | DG25-060-126 | 4 | 44 (20.0) |
| 1/8" 3.0mm | 60 x 63 | 1524 x 1600 | DG30-060-063 | 8 | 28 (12.7) |
| | 60 x 126 | 1524 x 3200 | DG30-060-126 | 4 | 55 (25.0) |
| | 120 x 126 | 3048 x 3200 | DG30-120-126 | 1 | 110 (50.0) |
| 3/16" 5.0mm | 60 x 63 | 1524 x 1600 | DG50-060-063 | 4 | 42 (19.1) |
| | 60 x 126 | 1524 x 3200 | DG50-060-126 | 2 | 83 (37.6) |
| | 120 x 126 | 3048 x 3200 | DG50-120-126 | 1 | 165 (75.8) |

Standard Testing:

Tests are standard ASTM procedures. Specific information on any test results and the procedure used is available upon request.

Testing vs Operating Conditions:

All test methods provide a standardized procedure to measure specific effects under controlled conditions. The results of any test are not intended to have any direct correlation with service conditions.



Seal & Design
Corporate Headquarters
 Ph: (716)-759-3344
 Info@SealAndDesign.com
 www.SealAndDesign.com