



Garlock BLACK GYLON® 3530

MATERIAL PROPERTIES*

Color:	Black
Composition:	PTFE with graphite
Temperature², °F (°C)	
Minimum:	-450 (-268)
Continuous Max:	+500 (+260)
Pressure², Maximum, psig (bar):	1200 (83)
P x T (max.)², psig x °F (bar x °C)	
1/32 and 1/16":	350,000 (12,000)
1/8":	250,000 (8,600)
Flammability:	Will Not Burn
Bacterial Growth:	Will Not Support

TYPICAL PHYSICAL PROPERTIES*

ASTM F36	Compressibility, %:	7-17
ASTM F36	Recovery, %:	40
ASTM F38	Creep Relaxation, %:	29
ASTM F152	Tensile, Across Grain, psi (N/mm²):	3000 (21)
ASTM D792	Specific Gravity:	2.16
ASTM D1708	Modulus @ 100% Elongation, psi (N/mm²):	2000 (13.8)
ASTM D149	Dielectric Properties, range, volts/mil.	
	Sample conditioning	<u>1/16" & Under</u> <u>1/8"</u>
	None	<2 -
	96 hours at 100% Relative Humidity	- -
ASTM F586	Design Factors	<u>1/16"</u> <u>1/8"</u>
	"m" factor:	2.8 2.0
	"y" factor, psi (N/mm ²):	1650 (11.4) 1650 (11.4)

SEALING CHARACTERISTICS*

	ASTM F37B Fuel A	DIN 3535- 4 Gas Permeability
Gasket Load, psi (N/mm²):	1000 (7)	4640 (32)
Internal Pressure, psig (bar):	9.8 (0.7)	580 (40)
Leakage	0.02 ml/hr.	<0.015 cc/min

Notes:

This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-104; properties based on 1/32" (0.8mm) sheet thickness unless otherwise mentioned.

* Values do not constitute specification Limits

² Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum PxT, consult Garlock Applications Engineering.



Seal & Design
Corporate Headquarters
 Ph: (716)-759-3344
 Info@SealAndDesign.com
 www.SealAndDesign.com