



Flexible Graphite SLS

- Graphite Adhesively Bonded to a .002" 316 Stainless Steel Foil
- Highly Compressible & Compactible
- Excellent Anti-Stick Properties
- Low Gas Permeability
- Low Electrical Resistance

Typical values refer to 1/16" material unless otherwise specified.

See graphs for temperature & pressure limits




Creep Relaxation ASTM F38B (1/32")	10%
Sealability ASTM F37A (1/32")	0.5 ml/hr
Compressibility ASTM F36A	40-45%
Recovery ASTM F36A	10-15%
Purity of Graphite	95% minimum
Leachable Chloride Content FSA Method (Typical)	50 ppm
Density DIN3754	70 lb/ft ³ (1.1 g/cc)
Color (Top/Bottom)	Silver
Special Feature:	Anti-Stick Coating Available Call 1.800.990.7325 for additional information.


Pressure & Temperature Graphs

Material Thickness: 1/16"

Liquids



Gases & Steam



The pressure/temperature graphs shown are the most current method of determining the suitability of a gasket material in a known environment. Use the pressure and temperature graphs to select the most suitable material for your application.

- 1. In area one, the gasket material is suitable using common installation practices subject to chemical compatibility.
- 2. In area two, appropriate measures are necessary for installation of the gasket to ensure maximum performance. Please call or refer to the KLINGER® expert software system for assistance.
- 3. In area three, do not install gaskets in these applications without first referring to the KLINGER® expert software system or contacting Thermoseal Inc.'s technical support service

These graphs were developed from testing Klinger materials. Do not use them for competitors' materials since non-asbestos gasketing materials do not have service equivalents.

Use: The limitations of use, as shown in the graphs, are for guidance only, and are based on 1/16" thick material. The limitations of use decrease significantly as gasket thickness increases. Do not use a thicker gasket material or "double gaskets" to solve a gasket problem without first consulting the manufacturer. The ability of a gasket material to make and maintain a seal depends not only on the quality of the gasket material, but also on medium being sealed, the flange design, the amount of pressure applied to the gasket by the bolts and how the gasket is assembled into the flanges and tightened. **Thermoseal engineers can advise on gasket selection and installation based on specified operating conditions. If you are in any doubt, fax us at 937.498.4911 or phone us at 937.498.2222.**

Seal & Design Able Division

5533 Steeles Avenue West Unit 11
Toronto, Ontario M9L 1S7
Ph: (416) 741-0750
Gasket@AbleSealAndDesign.com

Seal & Design Corporate Headquarters

4015 Casilio Parkway
Clarence, NY 14031
Ph: (716) 759-2222
Info@SealAndDesign.com
www.SealAndDesign.com

Seal & Design Higbee Division

6741 Thompson Rd N
Syracuse, NY 13221
Ph: (315) 432-8021
Sales@Higbee-Inc.com