

NV-519

Standard/Nonasbestos Gasket Material

F332949M8

Description:

NV-519 is a cellulose fiber material with thermoset resin and nitrile butadiene rubber binder. It has excellent tensile strength, crush resistance, and erosion resistance against high volume fluid flow and impingement. It is used primarily in automatic transmission valve body, pump, and accumulator/channel plate applications as well as carburetors and air compressors. It is intended for use in applications with short duration maximum temperatures up to 180°C (350°F).

Specification Properties:

Property	Value	Method
Density, g/cc(lb/cu.ft)	0.96 (60) (min.)	ASTM F 1315
Compressibility, % (at 6.9MPa)	5 - 15	ASTM F 36
Recovery, %	60 (min.)	ASTM F 36
Tensile Strength, AMD, MPa(psi)	27.59 (4000) (min.)	ASTM F 152
Fluid Resistance, IRM903 Oil		ASTM F 146
Change in Thickness, %	10 (max.)	
Change in Weight, %	30 (max.)	
Fluid Resistance, Dexron VI		ASTM F 146
Change in Thickness, %	10 (max.)	
Change in Weight, %	30 (max.)	
Fluid Resistance, Distilled Water		ASTM F 146
Change in Thickness, %	70 (max.)	
Change in Weight, %	70 (max.)	
Binder Type	Fully Cured Nitrile Butadiene	

Remarks and Related Documents:

Specification values determined by the test methods required for ASTM F-104, Type 3 materials.

EnCore®, Hydro-Fused®, MicroPore®, Pro-Formance®, Select-a-Seal®, Synthesseal®, Thermo-Tork®, and Voltoid® are registered trademarks of Interface Performance Materials, Inc. Select-a-Shield is a trademark of Interface Performance Materials, Inc.

WARNING: The description and performance data provided herein constitute a material specification for quality control purposes, but do not imply suitability for use in a specific application. Your specific application should not be undertaken without independent study and evaluation for suitability. Failure to select proper sealing products may result in either property damage or personal injury. For specific application recommendations, contact Interface Performance Materials. INTERFACE PERFORMANCE MATERIALS EXPRESSLY DISCLAIMS ALL WARRANTIES EITHER EXPRESS OR IMPLIED, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO EVENT WILL ISI BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, CONSEQUENTIAL OR PUNITIVE DAMAGES, HOWEVER CAUSED AND ON ANY THEORY OF LIABILITY, WHETHER IN CONTRACT, STRICT LIABILITY, OR TORT (INCLUDING NEGLIGENCE OR OTHERWISE) ARISING IN ANY WAY OUT OF THE USE OF THE INFORMATION CONTAINED IN ITS SPECIFICATION DATA SHEETS, ITS PRODUCTS OR THEIR FUTURE USE BY YOU OR ANY THIRD PARTIES, EVEN IF ADVISED OF THE POSSIBILITY OF SUCH DAMAGE.

Specification Data Sheet

Revised 07/01/15

©2015 Interface Performance Materials, Inc.

**Seal & Design
Corporate Headquarters**

Ph: (716)-759-3344

Info@SealAndDesign.com

www.SealAndDesign.com

For more information, please visit
www.InterfaceMaterials.com or contact

WORLD HEADQUARTERS
Interface Performance Materials, Inc.
216 Wohlsen Way
Lancaster, PA 17603
USA
+1.717.207.6000

TECHNICAL CENTER
Interface Performance Materials, Inc.
215 Wohlsen Way
Lancaster, PA 17603
USA
+1.717.207.6000

NORTH AMERICA
Interface Performance Materials, Inc.
22260 Haggerty Road, Suite 200
Northville, MI 48167
USA
+1.248.596.2800

ASIA PACIFIC
Interface Sealing Solutions Shanghai Co., LTD
Unit 14F, No. 728
Yan An Road West, Changning District
Shanghai 200050
China
+8621.5238.5650

EUROPE & SOUTH AMERICA
Interface Sealing Solutions Europe
Lili Pean, Le Bourg
Bonloc 64240
France
+33.5.5929.1220

GERMANY
Interface Performance Materials
Altenkirchen GmbH
P.O. Box 12 63
Koblener Strasse
Altenkirchen D-57610
Germany
+49.2681.80020

Interface
Performance Materials