

# TS-9006

**Thermo-Tork®/Nonasbestos Gasket Material**

F729900E09M5

**Description:**

TS-9006 is a heavy-duty, high density gasket material with fully cured styrene butadiene rubber binder. It is recommended for use in oil, water, and steam applications with high flange pressures and short duration maximum temperatures up to 350°C (650°F).

**Specification Properties:**

<u>Property</u>	<u>Value</u>	<u>Method</u>
Density, g/cc (lb/cu.ft)	1.52 (95) (min.)	ASTM F 1315
Compressibility, % (at 34.5MPa)	5 - 20	ASTM F 36
Recovery, %	40 (min.)	ASTM F 36
Tensile Strength, AMD, MPa (psi)	10.34 (1500) (min.)	ASTM F 152
Fluid Resistance, IRM903 Oil		ASTM F 146
Change in Thickness, %	20 - 60	
Fluid Resistance, Fuel B		ASTM F 146
Change in Thickness, %	15 - 40	
Binder Type	Fully Cured Styrene Butadiene	

**Remarks and Related Documents:**

Specification values determined by the test methods required for ASTM F-104, Type 7 materials.

EnCore®, Hydro-Fused®, MicroPore®, Pro-Formance®, Select-a-Seal®, Synthesseal®, Thermo-Tork®, and Voltoid® are registered trademarks of Interface Performance Materials, Inc. Select-a-Shield is a trademark of Interface Performance Materials, Inc.

WARNING: The description and performance data provided herein constitute a material specification for quality control purposes, but do not imply suitability for use in a specific application. Your specific application should not be undertaken without independent study and evaluation for suitability. Failure to select proper sealing products may result in either property damage or personal injury. For specific application recommendations, contact Interface Performance Materials. INTERFACE PERFORMANCE MATERIALS EXPRESSLY DISCLAIMS ALL WARRANTIES EITHER EXPRESS OR IMPLIED, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO EVENT WILL ISI BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, CONSEQUENTIAL OR PUNITIVE DAMAGES, HOWEVER CAUSED AND ON ANY THEORY OF LIABILITY, WHETHER IN CONTRACT, STRICT LIABILITY, OR TORT (INCLUDING NEGLIGENCE OR OTHERWISE) ARISING IN ANY WAY OUT OF THE USE OF THE INFORMATION CONTAINED IN ITS SPECIFICATION DATA SHEETS, ITS PRODUCTS OR THEIR FUTURE USE BY YOU OR ANY THIRD PARTIES, EVEN IF ADVISED OF THE POSSIBILITY OF SUCH DAMAGE.

Specification Data Sheet

Revised 07/01/15

©2015 Interface Performance Materials, Inc.

**Seal & Design**  
**Corporate Headquarters**  
**Ph: (716)-759-3344**  
**Info@SealAndDesign.com**  
**www.SealAndDesign.com**

For more information, please visit  
[www.InterfaceMaterials.com](http://www.InterfaceMaterials.com) or contact

WORLD HEADQUARTERS  
 Interface Performance Materials, Inc.  
 216 Wohlsen Way  
 Lancaster, PA 17603  
 USA  
 +1.717.207.6000

TECHNICAL CENTER  
 Interface Performance Materials, Inc.  
 215 Wohlsen Way  
 Lancaster, PA 17603  
 USA  
 +1.717.207.6000

NORTH AMERICA  
 Interface Performance Materials, Inc.  
 22260 Haggerty Road, Suite 200  
 Northville, MI 48167  
 USA  
 +1.248.596.2800

ASIA PACIFIC  
 Interface Sealing Solutions Shanghai Co., LTD  
 Unit 14F, No. 728  
 Yan An Road West, Changning District  
 Shanghai 200050  
 China  
 +8621.5238.5650

EUROPE & SOUTH AMERICA  
 Interface Sealing Solutions Europe  
 Lili Pean, Le Bourg  
 Bonloc 64240  
 France  
 +33.5.5929.1220

GERMANY  
 Interface Performance Materials  
 Altenkirchen GmbH  
 P.O. Box 12 63  
 Koblenzer Strasse  
 Altenkirchen D-57610  
 Germany  
 +49.2681.80020

**Interface**  
 Performance Materials