

TS-9016

Thermo-Tork®/Nonasbestos Gasket Material

F729900E09M9

Description:

TS-9016 has a fully cured styrene butadiene rubber binder and a blend of Aramid and cellulose fibers. It is intended for oil and water applications with short duration maximum temperatures up to 290°C (550°F).

Specification Properties:

<u>Property</u>	<u>Value</u>	<u>Method</u>
Density, g/cc(lb/cu.ft)	1.44 (90) (min.)	ASTM F 1315
Compressibility, % (at 34.5MPa)	10 - 25	ASTM F 36
Recovery, %	40 (min.)	ASTM F 36
Tensile Strength, AMD, MPa(psi)	12.41 (1800) (min.)	ASTM F 152
Fluid Resistance, IRM903 Oil		ASTM F 146
Change in Thickness, %	25 - 65	
Fluid Resistance, Fuel B		ASTM F 146
Change in Thickness, %	10 - 40	
Binder Type	Fully Cured Styrene Butadiene	

Remarks and Related Documents:

Specification values determined by the test methods required for ASTM F-104, Type 7 materials.

EnCore®, Hydro-Fused®, MicroPore®, Pro-Formance®, Select-a-Seal®, Synthesseal®, Thermo-Tork®, and Voltoid® are registered trademarks of Interface Performance Materials, Inc. Select-a-Shield is a trademark of Interface Performance Materials, Inc.

WARNING: The description and performance data provided herein constitute a material specification for quality control purposes, but do not imply suitability for use in a specific application. Your specific application should not be undertaken without independent study and evaluation for suitability. Failure to select proper sealing products may result in either property damage or personal injury. For specific application recommendations, contact Interface Performance Materials. INTERFACE PERFORMANCE MATERIALS EXPRESSLY DISCLAIMS ALL WARRANTIES EITHER EXPRESS OR IMPLIED, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO EVENT WILL ISI BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, CONSEQUENTIAL OR PUNITIVE DAMAGES, HOWEVER CAUSED AND ON ANY THEORY OF LIABILITY, WHETHER IN CONTRACT, STRICT LIABILITY, OR TORT (INCLUDING NEGLIGENCE OR OTHERWISE) ARISING IN ANY WAY OUT OF THE USE OF THE INFORMATION CONTAINED IN ITS SPECIFICATION DATA SHEETS, ITS PRODUCTS OR THEIR FUTURE USE BY YOU OR ANY THIRD PARTIES, EVEN IF ADVISED OF THE POSSIBILITY OF SUCH DAMAGE.

Specification Data Sheet

Revised 07/01/15

©2015 Interface Performance Materials, Inc.

Seal & Design
Corporate Headquarters
Ph: (716)-759-3344
Info@SealAndDesign.com
www.SealAndDesign.com

For more information, please visit
www.InterfaceMaterials.com or contact

WORLD HEADQUARTERS
 Interface Performance Materials, Inc.
 216 Wohlsen Way
 Lancaster, PA 17603
 USA
 +1.717.207.6000

TECHNICAL CENTER
 Interface Performance Materials, Inc.
 215 Wohlsen Way
 Lancaster, PA 17603
 USA
 +1.717.207.6000

NORTH AMERICA
 Interface Performance Materials, Inc.
 22260 Haggerty Road, Suite 200
 Northville, MI 48167
 USA
 +1.248.596.2800

ASIA PACIFIC
 Interface Sealing Solutions Shanghai Co., LTD
 Unit 14F, No. 728
 Yan An Road West, Changning District
 Shanghai 200050
 China
 +8621.5238.5650

EUROPE & SOUTH AMERICA
 Interface Sealing Solutions Europe
 Lili Pean, Le Bourg
 Bonloc 64240
 France
 +33.5.5929.1220

GERMANY
 Interface Performance Materials
 Altenkirchen GmbH
 P.O. Box 12 63
 Koblenzer Strasse
 Altenkirchen D-57610
 Germany
 +49.2681.80020

Interface
 Performance Materials