

Material Properties: Simriz® 487 (FFKM)

NOTE - All testing done on AS568-214 size O-rings

Original Properties	Simriz 487
Color	Black
Hardness, Shore A, ASTM D2240	79
Tensile Strength, MPa, ASTM D412 Die C	18.7
Tensile Strength, psi, ASTM D412 Die C	2710
% Elongation change, ASTM D412 Die C	170
100% Modulus, Mpa, ASTM D412 Die C	8.6
100% Modulus, psi, ASTM D412 Die C	1245
Low Temperature Glass Transition Temperature, ASTM D3418	
Tg (degrees C)	0
Low Temperature Retraction, ASTM D1329	
TR-10, degrees C	0
Air Aging ASTM D573, 70 hrs. at 250°C	
Hardness change, Shore A, ASTM D2240	0
% Tensile Strength change, ASTM D1414	-13
% Elongation change, ASTM D1414	+24
% Weight loss, ASTM D573	1.0
Compression Set, ASTM D395 Method B and ASTM D1414	
% Permanent Set, 70 hrs. at 275°C	26
% Permanent Set, 300 hrs. at 275°C	44
% Permanent Set, 70 hrs. at 300°C	29
% Permanent Set, 300 hrs. at 300°C	43
Water Bomb Fluid Immersion, ASTM D471, 70 hrs. at 200°C	
% Volume change, ASTM D471	+1.9



**Seal & Design
Able Division**

5533 Steeles Avenue West Unit 11
Toronto, Ontario M9L 1S7
Ph: (416) 741-0750
Gasket@AbleSealAndDesign.com



**Seal & Design
Corporate Headquarters**

4015 Casilio Parkway
Clarence, NY 14031
Ph: (716) 759-2222
Info@SealAndDesign.com
www.SealAndDesign.com



**Seal & Design
Higbee Division**

6741 Thompson Rd N
Syracuse, NY 13221
Ph: (315) 432-8021
Sales@Higbee-Inc.com