

ThermaCool™

Thermal Interface Materials

ThermaCool™ K275

Thermally Conductive, Silicone Coated KAPTON® Tape

ThermaCool™ K275 is manufactured with a 0.025mm thick thermally conductive KAPTON® film. The film is coated on both sides with 0.051mm of thermally conductive acrylic pressure sensitive adhesive. K275 is provided in roll form with a release liner on both sides for ease of application. The product was designed to bond electrical components to heat sinks. K275 contains no halides or silicones.

Features/Benefits

- KAPTON polyimide film and silicone rubber provide excellent electrical isolation and high dielectric performance
- Thermally conductive adhesive provides excellent thermal transfer at low application pressures
- Adverse effects of surface roughness are minimized with the highly conformable pressure-sensitive adhesive
- Polyimide film provides excellent resistance to cut through
- Can be die cut to size from convenient roll format

Typical Properties

Property	K275	Test Method
Colour	White	—
Thickness mm (in.)	0.127 (5.0)	ASTM D1000
Thermal Conductivity W/m ⁻¹ K ⁻¹	0.40	ASTM E1530
Thermal Impedance @ 10 psi °C in. ² /W	0.10	ASTM E1530
Dielectric Strength volts	6500	ASTM D149
Adhesion to Steel N/cm (oz./in.)	3.3 (30.0)	ASTM D1000
Operating Temperature °C	-29 to +149	—

Applications

- Bonding electronic components to heat sinks where electrical isolation is critical
- Thermally conductive dielectric barrier
- Void filler where thermal transfer and electrical isolation is very important

Availability—Available as slit rolls or roll goods 406mm wide x 32.9m long.



Seal & Design
Corporate Headquarters
Ph: (716)-759-3344
Info@SealAndDesign.com
www.SealAndDesign.com

ThermaCool™ is a registered trademark.
KAPTON® is a registered trademark of DuPont Corporation.

The data listed herein fall within the normal range of product properties for the products described, but they should not be used to establish specification limits nor used alone as the basis of design. SAINT-GOBAIN assumes no obligation or liability for any advice furnished by it or for results obtained to these products. All such advice is provided gratis and Buyer assumes sole responsibility for results obtained in reliance thereon. SAINT-GOBAIN warrants that the material itself does not knowingly infringe any patent, but no license is implied nor is any further warranty made.

©2004 Saint-Gobain Performance Plastics Corporation
AFF-1275E-PDF-1004-SGCS