



# Double Coated Tapes

## 9731 • 9731RW



Technical Data

July, 2011

**Product Description** 3M™ Double Coated Tapes 9731 and 9731RW have a firm, silicone pressure sensitive adhesive coated on one side of a polyester film carrier and a high performance acrylic adhesive coated on the other side of the carrier.

### Construction

Product Number	Faceside <sup>1,4</sup> Adhesive Type/ Thickness	Carrier Type/ Thickness	Backside <sup>2,4</sup> Adhesive Type/ Thickness	Liner Color, Type, Print	Liner Caliper	Total Tape Thickness (w/o liner)
3M tape 9731	350/ 0.0016" (0.041mm)	Clear PET 0.001" (0.025mm)	Silicone Adhesive/ 0.0029" (0.07mm)	Faceside liner – Tan, Polycoated Kraft, no print Backside liner – Fluoropolymer non-silicone clear, PET	0.0042" (0.17mm)/ 0.0029" (0.07mm)	0.0055" (0.14mm)
3M tape 9731RW	Silicone Adhesive/ 0.0029" (0.07mm)	Clear PET <sup>3</sup> 0.001" (0.025mm)	350/ 0.0016" (0.041mm)	Faceside liner – Fluoropolymer non-silicone clear, PET Backside liner – Tan, Polycoated Kraft, no print	0.0029" (0.07mm)/ 0.0042" (0.17mm)	0.0055" (0.14mm)

**Note 1:** Faceside adhesive is on the interior of the roll, exposed when unwound.

**Note 2:** Backside adhesive is on the exterior of the roll, exposed when liner is removed.

**Note 3:** PET (Polyester).

**Note 4:** The caliper listed is based on a calculation from manufacturing controlled adhesive coat weights using a density of 1.012 g/cc.

# 3M™ Double Coated Tapes

9731 • 9731RW

## Typical Physical Properties and Performance Characteristics

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

Product Number	3M™ Double Coated Tapes 9731/9731RW Silicone Adhesive	3M Double Coated Tapes 9731/9731RW Acrylic Adhesive
<b>Adhesion to stainless steel</b>		
ASTM D3330 - 90 degree	Oz/in (N/100 mm)	Oz/in (N/100 mm)
- 15 minute RT	40 (44)	71 (77)
- 72 hour RT	42 (45)	93 (101)
- 72 hour 158°F	48 (52)	121 (132)
<b>Adhesion to other surfaces</b>		
ASTM D3330 - 90 degree, 2 mil al foil, 72 hour RT	Oz/in (N/100 mm)	Oz/in (N/100 mm)
ABS	39 (43)	74 (81)
Polycarbonate	42 (45)	60 (65)
Polypropylene	40 (44)	44 (48)
<b>Shear Strength</b>		
ASTM D3654 modified - (.5 inch <sup>2</sup> sample size)	minutes	minutes
1000 grams at 72°F	+10,000	6090
500 grams at 158°F	+10,000	+10,000
<b>Dielectric Strength</b>		
ASTM D1000 RMS Voltage/Thickness	8000 Volts	
<b>Resistivity (ASTM D257) @ 70°F, 50% RH</b>		
Volume	3.4 x 10 <sup>15</sup> Ω-cm	
Silicone Adhesive Surface	2.6 x 10 <sup>15</sup> Ω-cm	
Acrylic Adhesive Surface	7.4 x 10 <sup>15</sup> Ω-cm	
<b>Relative High Temperature Operating Ranges</b>		
Long Term (days, weeks)	250°F (121°C)	
Short Term (minutes, hours)	350°F (177°C)	

## Available Sizes

(Subject to Minimum order requirements)

<b>Maximum Length</b>	
1/4" to 3/8"	36 yds. (32.9 m)
1" to 38"	108 yds. (98.9 m)
<b>Available Widths</b>	
Minimum	1/4" (6.35 mm)
Maximum	38" (965 mm)
<b>Normal Slitting Tolerance</b>	± 1/32 in. (0.08 mm)
<b>Core Size</b>	3.0 in. (76.2 mm)

# 3M™ Double Coated Tapes

9731 • 9731RW

---

## Features

- Silicone adhesive provides good bond to silicone rubber, strong holding power to various silicone surfaces, good temperature performance and good solvent resistance.
- 3M™ Adhesive 350 provides very high adhesion to a wide variety of materials, excellent shear holding power, high temperature resistance and excellent UV resistance.
- A thin polyester carrier provides dimensional stability and improved handling with ease of die cutting and lamination compared to adhesive transfer tapes.

---

## Application Techniques

Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improves bond strength.

To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Some typical surface cleaning solvents are isopropyl alcohol or heptane.\*

Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

**\*Note:** Carefully read and follow the manufacturer's precautions and directions for use when working with solvents. These cleaning recommendations may not be in compliance with the rules of certain air quality management districts in California; consult applicable rules before use.

---

## Application Ideas

- Applications where bonding silicone rubber to high surface energy materials is necessary.

---

## Application Equipment

To apply adhesives in a wide web format, lamination equipment is required to ensure acceptable quality. To learn more about working with pressure-sensitive adhesives please refer to technical bulletin, *Lamination Techniques for Converters of Laminating Adhesives* (70-0704-1430-8).

For additional dispenser information, contact your local 3M sales representative, or the toll free 3M sales assistance number at 1-800-362-3550.

# 3M™ Double Coated Tapes

9731 • 9731RW

---

<b>Storage</b>	Store in original cartons at 70°F (21°C) and 50% relative humidity.
<b>Shelf Life</b>	If stored under proper conditions, product retains its performance and properties for 18 months from date of manufacture.
<b>Certification/ Recognition</b>	<b>MSDS:</b> 3M has not prepared a MSDS for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, these products should not present a health and safety hazard. However, use or processing of these products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards.
<b>Technical Information</b>	The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.
<b>Product Use</b>	Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.
<b>Warranty, Limited Remedy, and Disclaimer</b>	Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.
<b>Limitation of Liability</b>	Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

---

ISO 9001:2008

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2008 standards.



**Seal & Design  
Able Division**  
5533 Steeles Avenue West Unit 11  
Toronto, Ontario M9L 1S7  
Ph: (416) 741-0750  
Gasket@AbleSealAndDesign.com



**Seal & Design  
Corporate Headquarters**  
4015 Casilio Parkway  
Clarence, NY 14031  
Ph: (716) 759-2222  
Info@SealAndDesign.com  
[www.SealAndDesign.com](http://www.SealAndDesign.com)



**Seal & Design  
Higbee Division**  
6741 Thompson Rd N  
Syracuse, NY 13221  
Ph: (315) 432-8021  
Sales@Higbee-Inc.com